


Avila



Colour Range




Angel




White



Chalk




Canvas



Pewter




Charcoal



Black



Vivid



Lightning

Internal Blockout Fabric

Roller Blind | Roman Shade | Panel Glide
3.0m width

Technical Information

Blockout

Composition:	100% Polyester
Thickness:	0.46mm ± 10%
Weight:	415 gsm ± 10%
Cutting*:	Ultrasonic, Aeronaut cut
Colourfastness:	6-7 Blue Scale (AS 2001.4.21)
Features:	Proudly Made in Australia

Fire Retardancy Information for NON FR Products[^]: Suitable for all building classes **except** Class 9(b) entertainment venues. A summary of BCA requirements can be provided on request.
[^] Fabrics which are not FR treated, have been FR tested and have a Flammability result over 6 or fabrics which are not FR treated and have not undergone FR testing.

Range:	Item:	Width:	Roll Length:
	Blockout - 82.633.9XX	3000mm	27 metres

Care & Cleaning Dusting with a feather duster is all that is required to keep your fabric looking good. For the removal of stains, dirt and grime, gently wipe fabric skins with a sponge soaked in lukewarm water. If marks are still visible, add a little detergent. Then dry gently with a clean cloth. Test in inconspicuous area before spot cleaning.

Thermal & Visual Properties

Colour	Thermal Comfort			Glazing & Fabric				Visual Comfort
	Ts	Rs	As	GTOT A	GTOT B	GTOT C	GTOT D	TL / TV
White	0	64	36	33.3	36.2	35.6	25	0
Pewter	0	69	31	30.8	34	34.2	24.6	0
Black	0	66	34	32.9	35.8	35.4	24.9	0

Solar protection indicators are laboratory-tested.

The most relevant and widely used thermal comfort factors include:

THERMAL COMFORT

Fabric Only
 Ts Solar Transmittance (%)
 Rs Solar Reflectance (%)
 As Solar Absorbance (%)
Solar radiation is always partially transmitted through, absorbed or reflected by the fabric. The sum of all 3 equals 100. Ts + Rs + As = 100% of solar energy.

GLAZING & FABRIC

Test data has been supplied using the following glazing types:
 •A Clear single glazing (4mm float)
 •B Clear double glazing (4mm float + 12mm space + 4mm float)
 •C Double glazing low-e coating and argon filled (4mm float + 16mm space + 4mm float)
 •D Reflective double glazing with low-e coating and argon filled (4mm + 16mm space + 4mm float)

GTOT (RANGE 0-1)

The Solar Heat Gain Coefficient (SHGC), measures the window's (fabric and glass) ability to transmit solar energy into a room. The SHGC is commonly referred to as g-tot. SHGC/g-tot is a calculation of the g-values of the solar protection device (fabric) and the glazing (A, B, C, D). The lower the GTOT value, the greater its ability to insulate against solar heat build-up.

VISUAL COMFORT

Fabric Only
 TL / TV Light Transmittance (%)
 RL Light Reflectance (%)

The fenestration property tests were conducted in accordance with EN 410 (1998), EN 14501:(2005), and EN 14500:(2008).

For more information contact our customer service team or visit: hunterdouglas.com.au/enquiry

turnilscollage.com.au